

Shenzhen All Technology Co., Ltd

Tel: +86-755-89896797 Fax: +86-755-28851555

Specification confirmation

| Product name | LiFePO4 battery pack |
|-----------------|----------------------|
| Product model | FPLi25.6100 |
| Customer code | |
| Document number | |
| Version number | V1.0 |
| Issue date | 2023-02-08 |

| Approved by | Reviewed by | Prepared by |
|---------------|-------------|-------------|
| Song Guo Song | Hai Yang | Kui Yuan |

| | Autograph | Date |
|-----------------------|---------------|------|
| | | |
| Customer confirmation | Company Name: | |
| | Company Seal: | |

Content

| 1. Scope | 2 |
|-----------------------------------|---|
| 2. Product Pict | 2 |
| 3. Basic parameters of battery | 2 |
| 4. PCM Configuration | 3 |
| 5. BMS Protection Parameters | 3 |
| 6. Cell technical parameters | 5 |
| 7. 2D diagram of the cell | 5 |
| 8. Electrical performance | 6 |
| 9. Use warning | 7 |
| 10. Battery operation instruction | 8 |
| 11. Other The Chemical Reaction | 9 |
| Note: | 9 |

1. Scope

This specification describes the basic performance, technical requirement, testing method, warning and caution of Li- ion rechargeable battery. The specification only applies to Shenzhen All Technology Co., Ltd


1.1 Application Scope

"General specification of lithium-ion battery for celluar phone" GB/T 18287-2013.

" Lithium ion cells and batteries used in portable electronic equipments — Safety requirements" GB 31241-2014

Electrotechnical terminology - Primary and secondary cells and batteries "GB/T 2900.41-2008

2. Product Pict



3. Basic parameters of battery

| Battery Model | IFP50160115 |
|--|---|
| Battery PACK | 8S1P |
| Size (L*W*H)mm | 522x238x203mm |
| Weight (kg) | ≤20Kg |
| Battery Rated Capacity (0.2C) | 100Ah |
| Battery Rated Voltage | 25.6V |
| Rated Power | 2560Wh |
| Operating Voltage Range | 20-29.2V |
| Battery Type | LiFePO4 |
| Standard Charge | CC/CV |
| Standard chargin currentg | 20A (0.2C) |
| Continuous Charging Current (Max.) | 100A (1C) |
| Standard discharge current | 20A(0.2C) |
| Continuous Discharge Current (Max.) | 100A (1C) |
| Peak Discharge Current | 200A(3S) |
| Internal Resistance (mΩ) | ≤50 mΩ |
| Storage Temperature | Standard Charge: -20°C~40°C Within 6 months: -20-35°C |
| Storage Humidity | 10%~90% RH |
| Shipping Voltage | 25V~26V |
| Charging Temperature | -20~70°C |
| Discharge Temperature | -20~75°C |
| Power consumption | ≤100uA |
| Discharge cut-off voltage | 20V |
| Cooling Mode | Natural Cooling |

| Waterproof Level | IP65 | | |
|-------------------------------------|--|---|------------|
| Battery Cycle Life | 6000 times (standard charge and discharge) | | |
| | Temperature | : | 23±5°C |
| Standard Environmental Condition | Humidity | : | 45-75%RH |
| | Atmospheric Pressure | : | 86-106 KPA |

4. Battery pack Materials BOM (Main material)

| Part Name | QTY | Description | Remarks |
|-----------|-----|----------------------------------|---------|
| Cell | 1 | IFR41100140 | |
| PCM | 1 | JBD-ZP04S005-L4S-60A- 60A-B-T | |
| Shell 1 | | Case size:520x239x203 mm | |
| | | | |
| | | | |

5. BMS Protection Parameters


| Function | Project | Specification | | | Unit |
|---------------------------------|--|--|---------------|-----------------|------------|
| Function | rioject | MIN | TYP | MAX | Omt |
| | Overvoltage protection voltage | 3.70 | 3.75 | 3.80 | V |
| Cell Overvoltage Protection | Overcharge protection delay time | 1000 | 2000 | 3000 | mS |
| | Overcharge protection restores voltage | 3.55 | 3.60 | 3.65 | V |
| | Over-discharge protection voltage | | 2.20 | 2.30 | V |
| | Over-discharge protection delay time | 1000 2000 3000 | | mS | |
| Cell Over-discharge protection | Over-discharge protection recovery voltage | 2.50 | 2.60 | 2.70 | V |
| | Over-discharge protects recovery conditions | The voltage recovers or the charge resun | | | ge resumes |
| | Charge overcurrent protection value | 105 110 | | 115 | A |
| Charging overcurrent protection | Charging overcurrent delay | 7 | 10 | 13 | S |
| | Charging overcurrent discharge conditions | Au | tomatic recov | er after a dela | y of 32S |

| | 1 | | 1 | i | |
|---|--------------------------------------|------------------|-------------------|-------------------|---------------|
| | 1st Overcurrent Discharge | 105 | 110 | 115 | A |
| | 1st Overcurrent Discharge delay | 7 | 10 | 13 | S |
| Overcurrent Discharge | 2nd Overcurrent Discharge | 400 | 560 | 720 | A |
| | 2nd Overcurrent Discharge delay | 150 | 320 | 500 | mS |
| | Overcurrent Discharge Release | Auto | matic recovery | after a delay o | f 32S |
| | Short circuit protection current | 320 | 360 | 400 | A |
| | Short circuit protection delay time | 200 | 400 | 800 | uS |
| Short Circuit Discharge | Short circuit protection recovery | Recover | after 5S delay | after disconne | cting the |
| | Short circuit description: s | hort circuit cui | rrent less than t | he minimum o | r higher than |
| | the maximum value may | cause short circ | cuit protection t | failure, short ci | rcuit current |
| | more than 1000A, there | is no guarante | e of short circu | it protection, a | nd it is not |
| | recomme | ended to do sho | ort circuit prote | ction test. | |
| Discharge high | Temperature protection value | 70 | 75 | 80 | °C |
| temperature protection (external) | Temperature protection release value | 60 | 65 | 70 | °C |
| Discharge Low Temperature protection | Temperature protection value | -25 | -20 | -15 | °C |
| (external) | Temperature protection release value | -15 | -10 | -5 | °C |
| High temperature charging protection | Temperature protection value | 60 | 65 | 70 | °C |
| (external) | Temperature protection release value | 50 | 55 | 65 | °C |
| Low temperature charging protection | Temperature protection value | -15 | -10 | -5 | °C |
| (external) | Temperature protection release value | -10 | -5 | 0 | °C |
| FET discharge high temperature protection | Temperature protection value | 85 | 90 | 95 | °C |
| (built-in curing) | Temperature protection release value | 50 | 65 | 80 | °C |
| | Balanced opening voltage | 3.25 | 3.3 | 3.35 | V |
| | Opening voltage difference | | 15 | | mV |
| Balanced function | Balanced current | 10 | | 70 | mA |
| | Balanced mode | | Charge Balance | | |
| | Balanced type | Tin | ne-sharing Bala | nce/Pulse Bala | nnce |

6. Cell technical parameters

| No. | Item | | Parameter | Remark |
|-----|---|--------------|-------------|---|
| | Nomi | nal Capacity | 102Ah | (07.0)00 0 1 1 1 |
| 1 | 1 Typical Voltage AC Impedance Resistance(1KHz) | | 3.2V | (25±2)°C, Standard charge and discharge |
| | | | ≤13mΩ | discharge |
| | | thickness | 50.2 ±0.3mm | |
| 2 | Dimension | width | 160.2±0.3mm | |
| | | height | 118±0.3mm | |
| 3 | Battery weight | | 1.93kg±37g | |

7. 2D diagram of the cell





8. Electrical performance

| No. | Item | Requirements | Measuring Procedure |
|-----|---------------------------------------|---|--|
| 1 | Rate Discharge Performance at 25°C | Discharge capacity/nominal capacity×100% A) 0.5CA ≥100% B) 1.0CA ≥98% | After standard charge and 1h rest, discharge to 10V cutoff with the current of 0.5C(A), 1.0C(A), respectively. If the discharge capacity fails to meet the technical requirements, this test is allowed to be repeated three times |

| | 2 | Discharge Performance at different temperature | Discharge capacity/nominal capacity×100% A)55°C 1.0C≥95% B)-20°C 1.0C≥70% | Measure the initial capacity and state of the battery: A) after standard charge and 5h restate 55°C, discharge to 10V cutoff with the current of 1.0C(A); B) after standard charge at 25±2°C and 4h rest at -20°C±2°C, discharge to 8V cutoff with the current of 1.0C(A). |
|--|---|---|---|--|
| | 3 | Capacity Retention and Capacity Recovery at 25°C | Capacity Retention≥95% Capacity Recovery≥97% | Measure the initial capacity and state of the battery, after standard charge and stored for 28 days, discharge to 10V cutoff with the current of 0.5C(A), calculate the remaining capacity, the retention can be expressed as a percentage of nominal capacity. After standard charged and 30mins rest, calculate the discharging capacity (Ah), the recovery can be expressed as a percentage of nominal capacity. The recovery is measured with discharge current 0.5CA with10V cut-off at (25±2)°C. |
| | 4 | Cycle Life at 25℃ | ≥6000 cycle @1.0C/1.0C | Under the 200kgf clamp, after standard charged and 30mins rest, discharge to 10V cutoff with the current of 1.0C (A) at (25 ± 2) °C, and then start the next cycle, end with the capacity decreasing to 80% of the initial capacity. The number of cycles is defined as the cycle life of the battery. |
| | 5 | Cycle Life at 35°C | ≥2800 cycle @1.0C/1.0C | Under the 200kgf clamp, after standard charged and 30mins rest, discharge to 10V cutoff with the current of 1.0 C (A) at (35 ± 2) °C, and then start the next cycle, end with the capacity decreasing to 80% of the initial capacity. The number of cycles is defined as the cycle life of the battery. |
| | 6 | Cycle Life at 45°C | ≥1000 cycle @1.0C/1.0C | Under the 200kgf clamp, after standard charged and 30mins rest, discharge to 10V cutoff with the current of 1.0 C (A) at (45 ± 2) °C, and then start the next cycle, end with the capacity decreasing to 80% of the initial capacity. The number of cycles is defined as the cycle life of the battery. |
| | 7 | End of life management | capacity/nominal capacity <70% | During the use of the battery, the battery shall be stopped when the end of life regulations is exceeded. |
| | | | | |

9. Use warning

In order to use and handle the battery safely, please read the operating instructions carefully before use

- Do not expose the battery to the sun or throw it in a fire.
- When charging the battery, the positive and negative polarities cannot be reversed.
- Do not short-circuit the positive and negative poles of the battery pack with wires or other metal objects!
- Do not pierce the battery pack housing with nails or other sharp objects, and do not hammer or pedal the battery pack!

- Do not disassemble or deform the battery.
- Do not immerse the battery in water.
- Never place the battery pack in a microwave oven or pressure vessel!
- Do not use the battery pack in an extremely hot environment, such as in direct sunlight or in a car on a hot day. Otherwise, the battery pack will overheat, which will affect performance and shorten the life of the battery pack.
- Do not mix batteries of different manufacturers, types and models.
- Do not allow children to touch the battery.
- If the battery pack emits odor, heat, deformation, discoloration or any other abnormal phenomenon, do not use it. If the battery pack is in use or charging, immediately remove it from the car (electrical appliance) or charger and stop using it!
- If the electrolyte gets into the eyes after the battery leaks, do not wipe it, flush it with water immediately, and seek medical assistance immediately. If it is not handled in time, the eyes will be injured!

Charge and discharge

- The battery must be charged under suitable conditions.
- Never charge the battery with a faulty charger.
- The battery can't be charged continuously for more than 24H.
- Do not charge the battery pack in the presence of fire or extreme heat! Do not use or store battery packs near heat sources such as fire or heaters! If the battery leaks or emits peculiar smell, immediately move it away from the open flame. When using the battery for the first time, fully charge the battery before using it.
- During the charging and discharging process of the battery pack, if there is an odor or abnormal sound, please stop charging and discharging immediately.
- The ambient temperature will affect the discharge capacity. When the ambient temperature exceeds the standard environment (25±5°C), the discharge capacity will be reduced!

Storage

• The battery is stored in a ventilated and dry environment.

Disposal

• The laws and regulations of different countries are different, and the disposal should be based on the local laws and regulations.

10. Battery operation instruction

10.1 Charging

Charging current: The maximum charging current specified in the specification cannot be exceeded.

Charging voltage: cannot exceed the highest limit voltage specified in the specification.

Charging temperature: The charging temperature of the battery must be performed in accordance with the temperature ranges of the specification. Charge in constant current and then in constant voltage mode, and reverse charging is prohibited. It is dangerous to charge the battery with the polarity reversed.

10.2 Discharging current

The discharge current of the battery cannot exceed the maximum discharge current specified in the specification.

Excessive current discharge will cause the battery to heat up and reduce its capacity.

10.3 Discharge temperature

The battery discharge temperature must be performed within the temperature range of the specification.

10.4 Over-discharges

Short-term overcharge and over-discharge will not affect the use of the battery, but long-term over-discharge will affect the function of the battery, and the battery will be permanently unsuitable. Another reason why the battery may be over-discharged is the disappearance of automatic energy. The way to prevent battery over-discharge is that the battery should maintain a certain amount of power.

10.5 Storage battery

The battery is stored within the temperature range specified in the specification. If the battery is stored for more than six months, it is recommended that you start charging the battery.

11. Other The Chemical Reaction

Since the battery uses the principle of chemical reaction, the performance of the battery will decrease with time, even if it is stored for a long time without use. If the conditions of use such as charging, discharging and ambient temperature are not within the specified range of use, the service life of the battery will also be shortened, or liquid leakage will result in equipment damage. If the battery cannot be charged for a long period of time, even if the charging method is correct, the battery needs to be replaced.

Note:

Matters not included in this manual shall be determined by mutual agreement.